



The  
Patent  
Office

PCT/GB 99/04170  
09/857852

INVESTOR IN PEOPLE

GB 99/ 4170

The Patent Office  
Concept House  
Cardiff Road  
Newport

South Wales  
NP10 8QQ  
JAN 2000


WPO PCT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



*P. Mahoney*

Signed

Dated 12 January 2000

**PRIORITY  
DOCUMENT**

SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH RULE 17.1(a) OR (b)

*This Page Blank (uspto)*

12 DEC 1998

# Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road  
Newport  
Gwent NP9 1RH

1. Your reference RFD/7086

2. Patent application number  
(The Patent Office will fill in this part)

12 DEC 1998

9827308.9

3. Full name, address and postcode of the or of each applicant (underline all surnames)

Peter James Boatman, 4 Hardings Cottages,  
St. Thomas, Exeter, EX4 1HD, United Kingdom.

Patents ADP number (if you know it)

75 68 652001

If the applicant is a corporate body, give the country/state of its incorporation

4. Title of the invention

Improvements in or Relating to Pipes

5. Name of your agent (if you have one)

Swindell & Pearson

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

48 Friar Gate,  
Derby DE1 1GY

Patents ADP number (if you know it)

00001578001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number  
(if you know it)

Date of filing  
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing  
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

- a) any applicant named in part 3 is not an inventor, or
  - b) there is an inventor who is not named as an applicant, or
  - c) any named applicant is a corporate body.
- See note (d))

**Patents Form 1/77**

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form	0
Description	5 ✓
Claim(s)	0
Abstract	0
Drawing(s)	11-10

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*)

Request for preliminary examination and search (*Patents Form 9/77*)

Request for substantive examination (*Patents Form 10/77*)

Any other documents  
(please specify)

11.

I/We request the grant of a patent on the basis of this application.

Signature

*Swindell & Pearson*  
Swindell & Pearson

Date 11/12/98

12. Name and daytime telephone number of person to contact in the United Kingdom

R. F. Drever - 01332 367051

**Warning**

*After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.*

**Notes**

- a) If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- b) Write your answers in capital letters using black ink or you may type them.
- c) If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- d) If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- e) Once you have filled in the form you must remember to sign and date it.
- f) For details of the fee and ways to pay please contact the Patent Office.

## Improvements in or Relating to Pipes

This invention is concerned with improvements in or relating to pipes and a method of manufacturing same, particularly corrosion resistant pipes adapted for use with liquids having high chemical concentrations or of a corrosive nature and in ground having a corrosive nature.

According to the present invention there is provided a pipe comprising a plurality of material layers, a core layer being formed of a composite material formed by a coalescence of materials, including an aggregate of materials providing strength and rigidity and a bonding agent, (hereinafter referred to as plastic concrete), and outer layers on respective sides of the core layer, each of the outer layers being formed of a plastics material.

The present invention further provides a method of manufacturing a pipe, the method comprising forming a pair of material layers from a plastics material, positioning the material layers in a spaced apart relation, and forming a core layer between the preformed material layers.

The core layer may be formed of plastic concrete and may be introduced in a flowable state between the preformed material layers to be moulded therein. The preformed material layers provide formwork for the moulding. The preformed material layers are moulded and are retained in their moulds to provide the formwork for moulding of the core layer.

The plastic concrete may be adjusted so as to commence curing within a short time of being introduced between the preformed material layers, whereby lower layers of the plastic concrete cure when further layers of the plastic concrete are introduced.

The present invention also provides a mould assembly for moulding a pipe, the assembly comprising a plurality of moulds formed of polymer concrete.

An embodiment of the present invention will now be described by way of example only, with reference to the accompanying drawing, the single figure of which is a diagrammatic section through a mould assembly for producing a pipe.

A pipe, for use as a sewage pipe, is formed by producing a sandwich construction in the form of two preformed laminates on respective sides of a core material. The laminates may each be formed from a synthetic resin and the core may be a composite material formed from plastic concrete which provides the required stiffness and strength for the structure. The bonding agent is a thermosetting resin, for example polyester, epoxy, acrylic, vinylester, polyurethane or phenolic, or can be a thermoplastic resin, for example polyvinylchloride, polypropylene or polyurethane. The aggregate can be an inorganic material, for example any of silica sand, silica powder, calcium powder, gravel, stone chippings, ceramic powder or ceramic chippings, or any combination thereof. To provide further strength, other types of reinforcement can be included in the plastic concrete, such as glass, metal or plastic fibres. By using the same synthetic resin in forming the laminates and the core, the bond between the laminates and the core can be improved and the core becomes more of an integral part of the laminates.

Referring to the drawing, the two preformed laminates are in the form of reinforced plastic pipes or tubes 10, 12, formed either by filament winding a pipe, or by forming a sheet which is then rolled and bonded to form a tube. The inner tube 10 locates in the mould assembly to extend between a base ring mould 14 and the top ring mould 16. The outer tube 12 also extends between the moulds 14, 16, locating in respective slots in the ring moulds. A cone 18 locates above the mould 16 and assists in guiding the plastic concrete when it is poured into the annular space between the tubes 10, 12. The cone 18 also centrally locates the inner tube 10. After completion of the casting of the plastic concrete, as hereinafter described, the cone 18 is removed and a mould 20 is fitted, further plastic concrete then being poured into the gap between the pipe 10 and the mould 20 to form the top spigot of the pipe. All of the moulds 14, 16, 18 and 20 are held together by tie bars.

The moulds 14, 16, 18 and 20 are cast in polymer concrete so as to reduce costs. From one machined mould there can be cast numerous polymer concrete moulds so that the unit cost is lower and the polymer concrete moulds can be produced on site.

By adjusting the thickness and type of materials used in the inner and outer tubes 10, 12, the finished pipe can be designed to have different properties. In pressure pipes, the inner tube 10 can be designed to be strong enough to take all the pressure, the plastic concrete and the outer tube 12 providing stiffness and structural integrity.

By adjusting the mixture of the plastic concrete, the latter can start to cure within a few minutes of being poured. By also adjusting the volume of plastic concrete being poured and maintaining a constant vibration to ensure that the plastic concrete is consolidated and air pockets are removed, it is possible to cast pipes over 6 metres in length without providing any support to either of the inner or outer tubes 10, 12. Support is not required because the head of liquid plastic concrete changes as the lower layers of the plastic concrete cure. This also means that the thickness of the inner and outer tubes 10, 12, can be reduced to save costs. When using a pipe as a jacking pipe, the length is not important, being restricted to the size of the shaft and the machine. However when a pipe is used for conventional open trench laying, longer pipe lengths are preferred, reducing the number of joints and speeding up installation. The time to lay any length of pipe is basically the same, and as the weakest point of any pipe is the joint, the more joints there are, the more there are potential problems.

With previous methods of constructing pipes using plastic concrete, a pipe has required to have a large cross-section to be strong enough, thereby increasing the weight of the pipe. Although this does not cause a particular problem when the pipe is to be used as a micro tunnelling pipe, the weight of the pipe is important with conventional open trench applications. In many cases a crane cannot be positioned alongside where the pipe is to be laid and this means that in order to lift the pipe the crane would need to have its jib extended, which reduces its load carrying capabilities. Also with previous

methods an inner liner has had to be strong enough to resist buckling loads caused by the head of the plastic concrete when being poured. This increased cost and the liner cost often became as much as 75% of the cost of the finished pipe. Where a thick liner is used, pipe length is restricted, unless there is provided an internal support shutter which is difficult to manufacture and remove without damaging the inner liner. If a collapsible mandrel is used, this makes the mould cost prohibitive, and it is difficult to make a collapsible mandrel over 3 metres.

Further, if the plastic concrete was to be completed in stages, problems arise in achieving a suitable bond between the layers of plastic concrete. As the latter would be poured from the top, it would adhere to the liners and cure, so restricting the flow when the next batch of plastic concrete is poured. Also air pockets would be caused in the plastic concrete as the uncured plastic concrete would form around the previously cured material.

In addition, previous pipe mould assemblies have used metal shutters which are expensive to manufacture and are restricted in length, making it necessary to join segments together. Such joints make the overall shutter very heavy and often difficult to produce. An outer abrasive resistance surface for the pipe has to be applied to the inner face of the shutter by hand, which takes time, and the lining has to cure before the shutter mould can be assembled to the other moulds. Due to the weight of the shutter and its height, an overhead crane is required and it takes time to assembly and disassemble the shutter. Also previously, ring moulds have been machined out of steel and were therefore expensive and heavy, increasing cost.

A pipe which is manufactured as hereinbefore described, using the mould assembly of the drawing, can be easily produced on site and meets the following requirements:- lightweight but strong; low cost; corrosion resistant; easy to install; and available in large volumes. Large pipe projects stretch for many miles and transportation of pipe can be a big cost, particularly if the pipes have to be imported. To produce a pipe as hereinbefore described requires very little capital investment and no major infrastructure, only a covered area with a flat concrete floor. On completion, equipment can be



removed to another site.

Various modifications may be made without departing from the invention.

**This Page Blank (uspto)**